



Using CeramAlloy® HTP

PLEASE READ THESE INSTRUCTIONS AND SAFETY DATA SHEET (SDS) CAREFULLY PRIOR TO USE

METALCLAD® CeramAlloy® HTP is a two component, 100% solids polymer composite specifically formulated to rebuild and repair all types of fluid flow equipment that may be subject to elevated temperatures.

SURFACE PREPARATION

METALCLAD® CeramAlloy® HTP should only be applied to clean, dry and well-roughened surfaces.

1. Remove all loose material and surface contamination and clean with a suitable solvent which leaves no residue on the surface after evaporation such as acetone, MEK, isopropyl alcohol, etc.
2. Clean/roughen surface by abrasive blasting.
3. If necessary, apply moderate heat and/or allow the component(s) to 'leach' to remove ingrained contaminants.
4. Thoroughly roughen surfaces by abrasive blasting to achieve a 'white metal' degree of cleanliness and an anchor pattern of 3 mils.

Note: In situations where adhesion is not desired, such as when making molds and patterns or to ease future disassembly, apply a suitable release agent (mold release compound, paste wax, etc.) to the appropriate surfaces.

MIXING AND APPLICATION

Since the mixing ratio of the Base and Activator components is CRITICAL, the CeramAlloy® HTP Base and Activator have been supplied in precisely measured quantities. [Note: Should a small amount of material be required, it is imperative that both the Base and Activator components be measured precisely using the ratios provided.] Place the components on a clean mixing surface, keeping the Base and Activator separated until ready to mix and apply.

Using a spatula, putty knife or other appropriate tool, mix thoroughly until all streaks disappear, resulting in a uniform color and consistency. Spread material out in a thin layer over the mixing surface to force out any trapped air. This procedure will also maximize working time.

Some deeply eroded areas, e.g. cut-waters, impeller leading edges, diffuser vanes, etc. may require the use of reinforcement tape or other suitable means to bridge the damaged area(s) followed by the application of additional material.

Technical Data

Volume capacity per kg.	38 in ³ / 629 cc	
Mixed density	0.057 lbs per in ³ / 1.59 gm per cc	
Coverage rate per kg. @ 0.25 in - 6 mm	152 in ² / 0.098 m ²	
Shelf life	Indefinite	
Volume solids	100%	
Mixing ratio	Base	Activator
By volume	2.3	1
By weight	5	2

Working Life & Cure Times

Ambient Temperature	Working Life	Machining Light Load	Full Mechanical	Chemical Immersion
59°F 15°C	1.5 hrs	20 hrs	48 hrs	5 days
77°F 25°C	40 min	10 hrs	18 hrs	3 days
86°F 30°C	25 min	7 hrs	15 hrs	2 days

Physical Properties

	Typical Values		Test Method
Compressive strength	12,500 psi	875 kg/cm ²	ASTM D-695
Flexural strength	8,500 psi	595 kg/cm ²	ASTM D-790
Hardness - Shore D	87		ASTM D-2240
Tensile Shear Adhesion			
Steel	4000 psi	280 kg/cm ²	ASTM D-1002
Copper	2500 psi	175 kg/cm ²	ASTM D-1002
Stainless steel	3500 psi	246 kg/cm ²	ASTM D-1002

Chemical Resistance

Ammonia (5%)	EX
HCL (20%)	G
Motor oil	EX
NaCl (5%)	EX
Sulfuric acid (98%)	G
Sulfuric acid (50%)	EX

EX - Suitable for most applications including immersion.
G - Suitable for intermittent contact, splashes, etc.

Temperature Guidelines

Up to:
Dry - 520°F / 270°C
Wet - 330°F / 165°C

We would always recommend that elevated temperature applications be discussed with your local ENECON Fluid Flow Systems Specialist.

HEALTH & SAFETY

Every effort is made to insure that ENECON® products are as simple and safe to use as possible. Normal industry standards and practices for housekeeping, cleanliness and personal protection should be observed. For further information and guidance, please refer to the detailed MATERIAL SAFETY DATA SHEETS (MSDS) supplied with the material and also available on request.

CLEANING EQUIPMENT

Wipe excess material from tools immediately. Use acetone, MEK, isopropyl alcohol or similar solvent as needed.

TECHNICAL SUPPORT

The ENECON® engineering team is always available to provide technical support and assistance. For guidance on difficult application procedures or for answers to simple questions, call your local ENECON® Fluid Flow Systems Specialist or the ENECON® Engineering Center.

All information contained herein is based on long term testing in our laboratories as well as practical field experience and is believed to be reliable and accurate. No condition or warranty is given covering the results from use of our products in any particular case, whether the purpose is disclosed or not, and we cannot accept liability if the desired results are not obtained.

Copyright © 2018 by ENECON Corporation. All rights reserved. No part of this work may be reproduced or used in any form or by any means - graphic, electronic, or mechanical including photocopying, recording, taping or information storage and retrieval systems - without written permission of ENECON Corporation.

ENECON[®] Corporation
The Fluid Flow
Systems Specialists.
www.enecon.com

Toll Free: 888-4-ENECON (888-436-3266)

Tel: 516 349 0022 · Fax: 516 349 5522

Email: info@enecon.com

6 Platinum Court · Medford, NY 11763-2251